

## Red Granular 0-0-60

CHEMICAL COMPOSITION			
Component	Symbol	Typical %	Guarantee
Potassium Oxide Equivalent	K <sub>2</sub> O	61.0	60% (min.)
Potassium Chloride	KCI	96.5	
Sodium Chloride	NaCl	2.8	
Chloride	Cl	47.6	
Moisture	H <sub>2</sub> O	0.02	

## PARTICLE SIZE DISTRIBUTION CUMULATIVE %

Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
4	4	4.75	0 - 2	0.5
5	5	4.00	3 - 15	8
6	6	3.35	20 - 50	37
7	7	2.80	50 - 75	63
8	8	2.36	75 - 95	88
9	10	2.00	93 - 100	98
10	12	1.70	98 - 100	99

PHYSICAL PROPERTIES				
Bulk Density (Loose)	Typical			
- lb/ft <sup>3</sup>	66			
- kg/m <sup>3</sup>	1054			
Angle of Repose	37 Degrees			

## SIZING CHARACTERISTICSParameterTypical2 mm x 4 mm (%)90Size Guide Number (SGN)305

53

Uniformity Index (UI)

## Please refer to the Safety Data Sheet (SDS #: MOS100052) for additional information (www.mosaicco.com)

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values Additional handling, transportation, or improper/extended storage may affect product analyses. Mosaic disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.